

Caustic and Acid Test Results

4 Days at a constant temperature between 60 - 70 Degrees C				
Chemical %	Seeflex 040	Seeflex 400W	LM4 Polyester	Teflex
Caustic 2%	No change to material	No Change to material	Very weak falling apart	No Change to material
Caustic 10%	Strength good, slight sign of cracking	No Change to material	Disintegrated	No Change to material
Acid AC300 2%	Yellow little bit fragile	No Change to material	Still in working order	No Change to material
Acid AC300 10%	Disintegrated	Starting to go green, material still has strength	Still in working order	No Change to material